



CLAYBURN REFRACTORIES LTD.

31543 KING ROAD
ABBOTSFORD, BC
CANADA V2T 5Z2
PHONE: (604) 859-5288
FAX: (604) 859-0424

TECHNICAL DATA

CLAYBURN-SET 50 DC

A mullite based wet air-set mortar in troweling or dipping consistencies. It is used in general applications with high alumina brick and high fired super duty brick and shapes.

Maximum Recommended Use Temperature	3100°F
--	--------

Chemical Analysis

Al ₂ O ₃	50.0%
SiO ₂	43.0%
Fe ₂ O ₃	0.7%